


DELTA SEAL™

Technical Data Sheet

DSB 1500 - 0.8mm (Board Based)

Revision: DSB1500-08172022

Product	DSB 1500 - 0.8mm (Board based)																	
Scope	0.75mm Folding Box Board/Polyolefin Film/20 micron lacquered Aluminium foil/reinforced heatseal coating for sealing to glass, PE, PP, PET and PVC.																	
Composition	<table border="1"> <thead> <tr> <th>Material</th> <th>Standard</th> <th>Metric</th> </tr> </thead> <tbody> <tr> <td>Folding Boxboard</td> <td>0.030"</td> <td>0.75mm</td> </tr> <tr> <td>Polyolefin Film</td> <td></td> <td></td> </tr> <tr> <td>Foil</td> <td>0.0008"</td> <td>0.020mm</td> </tr> <tr> <td>Reinforced Heat Seal</td> <td>35gsm (weight)</td> <td>35gsm (weight)</td> </tr> </tbody> </table>	Material	Standard	Metric	Folding Boxboard	0.030"	0.75mm	Polyolefin Film			Foil	0.0008"	0.020mm	Reinforced Heat Seal	35gsm (weight)	35gsm (weight)		
Material	Standard	Metric																
Folding Boxboard	0.030"	0.75mm																
Polyolefin Film																		
Foil	0.0008"	0.020mm																
Reinforced Heat Seal	35gsm (weight)	35gsm (weight)																
Adhesive or resin bonding layers not shown.																		
FDA Status:	Recommended Storage and Handling: Refer to website																	
Drug Master File (DMF):	EU / EP Reg.: 1935/2004/EX, 2023/2006/EC, 10/2011/EC																	
GTR Oxygen: Essentially Zero	MVTR: Essentially Zero																	
Print Location (if any): Surface of Foil																		

Selig materials are compliant with current USFDA Food allergen Guidelines.

Selig materials are compliant with California Proposition 65 labeling requirements.

Selig materials are compliant with limitation of heavy metals in packaging per CONEG & EU 94/62/EC, article 11.

MSDS's are not required as Selig is not a chemical manufacturer or distributor and our products are 'articles' intended for food packaging per 29 CFR 1910.1200 (HazCom).

The information contained within this product data bulletin is to be used as a general guide in determining which structures are offered for sealing to specific container materials. All of the information which we provide is reliable to the best of our knowledge, but the accuracy thereof is not guaranteed. We suggest that consumers determine suitability for their own application.